



# SYNTON-TECH CORPORATION

## METAL FILM FIXED RESISTORS

File No.:	MF-02
Version:	A
Page:	1/16
Date :	2006.01.01

### 1. INTRODUCTION

To fill the function gap of carbon film resistors, metal oxide film resistors or wirewound resistors SYNTON-TECH makes metal film resistors. The resistive element is a high contests of AL2O3 ceramic rod on which a thin film of Ni/Cr alloy is deposited by vacuum sputtering system. Then contact caps are pressed onto the ends of the rod and a helical groove cut through the film to give the required resistance value. Connecting copper wire are welded to the end caps. Finally the resistors are coated with multiple layers of insulation lacquer. **SYNTON-TECH's** MF series are suitable for all circuit applications especially tighter tolerance and low temperature coefficient are required.

### 2. FEATURES

- Meet American military specification MIL-R-10509F!
- Very low current noise!
- Major applications are switching power supplies, communications equipment, monitors, testing meters.

APPROVED	CHECKED	DESIGNED	REMARK	DOCUMENT NO.
Carol	May	Chen		0201010017

*Confidential, Do Not Disseminate.*



**SYNTON-TECH CORPORATION**


**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	2/16
Date :	2006.01.01

### 3. EXPLANATIONS OF ORDERING CODE

**DESCRIPTION : MF 1/4W 1% 100**

**SYNTON CODE : MF 025 F 1000 T**





**SYNTON-TECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	3/16
Date :	2006.01.01

### 4. ELECTRICAL CHARACTERISTICS

TYPE	MF-12	MF-25S	MF-40S	MF-25	MF-50S	MF-60S	MF-50	MF-100S	MF-100	MF-200S	MF-200	MF-300S
Power Rating at 70	1/16W 1/8W 1/6W	1/4W	0.4W	1/4W	1/2W	0.6W	1/2W	1W	1W	2W	2W	3W
Operating Temp. Range	—55 + 155											
Maximun Working Volt.	200V	250V	350V	250V	350V	350V	350V	500V	500V	500V	500V	500V
Maximun Overload Volt.	400V	500V	700V	500V	700V	700V	700V	1000V	1000V	1000V	1000V	1000V
Dielectric withstanding Volt.	400V	500V	700V	500V	700V	700V	700V	1000V	1000V	1000V	1000V	1000V
Value Range ±0.5%. ±1%	STANDARD 10 ~1M											
	SPECIAL Low to 0.1 high to 30Meg											
±0.25%	100 ~100K											
±0.1%	100 ~47K											
	SPECIAL VALUES AVAILABLE UPON REQUEST											
Temp. Coefficient	±10ppm/ 、 ±15ppm/ 、 ±25ppm/ 、 ±50ppm/ 、 ±100ppm/											

Figure 1



## 5. POWER RATING

(1)**Power Derating** : The rated power at the temperature in excess of 70 shall be derated in accordance with figure2





Figure2

## (2)Pulse Loading Characteristics





**SYNTON-TECH CORPORATION**

**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	5/16
Date :	2006.01.01

**(2)Rated Voltage :** The DC or AC(rms) continuous working voltage corresponding to the rated power is determined by the following formula:

$$E = \sqrt{R \times P}$$

Where E : Continuous rated DC or AC (rms) working voltage (v)

P : Rated power (w)


R : Resistance value ( )



**SYNTON-TECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	6/16
Date :	2006.01.01

**6. DIMENSIONS**



Unit: m/m

TYPE	POWER	L	D	H	d
MF-12	1/16W 1/6W 1/8W	$3.5 \pm 0.3$	$1.8 \pm 0.3$	$25 \pm 3$	$0.45 \pm 0.05$
MF-25S	1/4W				
MF-40S	0.4W				
MF-25	1/4W	$6.0 \pm 0.5$	$2.3 \pm 0.3$	$25 \pm 3$	$0.56 \pm 0.1$
MF-50S	1/2W				
MF-60S	0.6W				
MF-50	1/2W	$9.0 \pm 0.5$	$3.2 \pm 0.5$	$25 \pm 3$	$0.60 \pm 0.1$
MF-100S	1W				
MF-100	1W				
MF-200S	2W	$11 \pm 1.0$	$4.5 \pm 0.5$	$35 \pm 3$	$0.80 \pm 0.1$
MF-200	2W				
MF-300S	3W				
		$15 \pm 1.0$	$5.0 \pm 0.5$	$35 \pm 3$	$0.80 \pm 0.1$


Figure3



**SYNTON-TECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	7/16
Date :	2006.01.01

**(1) FORMING PACKING**



Unit : m/m

TYPE	Foming Type	P ± 1 (Min.)	H ±2.5 (Min.)	H1 ± 1 (Min.)	H2 ± 1 (Min.)	H3 ± 1 (Min.)	H4 ± 1 (Min.)	A1 ± 1 (Min.)	A2 ± 1 (Min.)	A0 ± 1 (Min.)	Remark
MF-12	M	5~	10~								MF-25S
	F							25±3		3	MF-40S
MF-25	M	10~	10~								MF-50S
	FK							25±3		3	MF-60S
MF-50	M	12.5~	10~								MF-100S
	FK	5~10							25±3	3	
MF-100	M	15~	10~	8~	3~	8~	5~				MF-200S
	MK.MB										
	FK F	5~10						5~	5~	3	
MF-200	M	20~	10~	8~	3~	8~	5~				MF-300S
	MK.MB										
	FK F	5~10						5~	5~	3	

Remark : 1. B = 1.15 ~ Z = 3 ±1. K = 2 ±0.5,

2. ALTERNATE MARKING METHOD ALSO AVAILABLE ON REQUEST.


Figure4



**SYNTECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	8/16
Date :	2006.01.01

**(2) TAPE PACKING (T-TYPE)**



Unit:m/m

TYPE	SIZE	T	P ±0.5	W ±0.5	D1-D2 Max.	E Max.	Z Max.	S Max.	I Min.
MF-12	T-26	26±1.0	5	6	0.8	1	1.2	1	3
MF-25S	T-52	52±2.0	5	6	0.8	1	1.2	1	3
MF-40S									
MF-25	T-26	26±1.0	5	6	1.0	1	1.2	1	3
MF-50S	T-52	52±2.0	5	6	1.0	1	1.2	1	3
MF-60S									
MF-50	T-52	52±2.0	5	6	1.2	1	1.2	1	3
MF-100S									
MF-100	T-74	74±2.0	5	6	1.4	1	1.2	1	3
MF-200S									
MF-200	T-74	74±2.0	10	6	1.4	1	1.2	1	3
MF-300S									

Figure5





## 7. CHARACTERISTICS

### (1) Insulation Resistance

Test Method : Resistors shall be clamped in the trough of a 90 degree metallic V-block, apply DC 100V between this electrode and another lead wire for 1 minute.

Acceptance Standard : 10,000 M ohm above

### (2) Terminal Strength

Test Method : Pull a resistor with a weight of 1 kg for 5 seconds. Bend the terminal lead wire with 500gs weight for 90 degree and bend it for 90 degree oppositely and return to normal.

Acceptance Standard : Resistance shall not change more than  $\pm 1\%$ .  
No evidence of mechanical damage.

### (3) Vibration

Test Method : Total amplitude of 1.5mm. The frequency shall vary from 10 HZ to 55 HZ, for approximate 1 second. Make this test in the direction parallel to the resistor axis, and up/down for 2 hours respectively. (altogether 6 hours.)

Acceptance Standard : Resistance shall not change more than  $\pm 1\%$ .  
No evidence of mechanical damage.

### (4) Short Time Overload

Test Method : Resistors shall be tested 2.5 times rated voltage for 5 seconds at ambient room temperature.

Acceptance Standard : Resistance shall not change more than  $\pm 0.5\%$ .  
No evidence of mechanical damage.



# SYNTON-TECH CORPORATION

## METAL FILM FIXED RESISTORS

File No.:	MF-02
Version:	A
Page:	10/16
Date :	2006.01.01

### (5) Load Life

Test Method : Thermostatic chamber at a temperature of  $70\pm 5$  under a rated DC voltage for 1.5 hours on and 1/2 hour off repeat this cycle for  $1000\pm 12$  hours.

Acceptance Standard : Resistance shall not change more than  $\pm 1\%$ .  
No evidence of mechanical damage.

### (6) Moisture Resistance

Test Method : At temperature of  $40\pm 2$  and a relative humidity of 90-95% for  $1000\pm 12$  hours, under a rating DC voltage for hours on and 1/2 hour off.

Acceptance Standard : Resistance shall not change more than  $\pm 1.5\%$ .  
No evidence of mechanical damage.

### (7) Temperature Cycling

Test Method :

STEP	1	2	3	4
TEMP	$-55\pm 3$	$20\pm 5$	$85\pm 2$	$20\pm 5$
TIME	30min.	10~15min.	30min.	10~15min.

Form 1 to 4 is a cycle as shown above, repeat 5 cycles  
Measure resistance after 1 hour in normal temperature.

Acceptance Standard : Resistance shall not change more than  $\pm 0.5\%$ .  
No evidence of mechanical damage.

### (8) Resistance to Soldering Heat

Test Method : Immerse each terminal wire of a resistor up to  $4\pm 0.8$ mm away from the resistor body in the solder tank at  $350\pm 10$  for  $3\pm 0.5$  seconds.  
Measure resistance in 3 hours.

Acceptance Standard : Resistance shall not change more than  $\pm 0.5\%$ .  
No evidence of mechanical damage.



# SYNTON-TECH CORPORATION

## METAL FILM FIXED RESISTORS

File No.:	MF-02
Version:	A
Page:	11/16
Date :	2006.01.01

### (9) Resistance to Solvent

Test Method : immerse a resistor completely in reagent at a temperature of 20~25 for 30±5 seconds.

Acceptance Standard : No evidence of mechanical damage.

### (10) Dielectric Withstanding Voltage

Test Method : Resistors shall be clamped in the trough of a 90 degree metallic V-block, apply AC between this electrode and another lead wire for 1 minute.

Acceptance Standard : Resistance shall not change more than ±1%.  
No evidence of mechanical damage.

### (11) Solderability

Test Method : apply flux to the terminal wire of a resistor up to 4±0.8mm away from the resistor body and immerse the flux applied portion in the solder tank at 260±5 for 3±0.5 seconds

Acceptance Standard : more than 95% of a circumference of the immersed portion shall be completely covered with new solder.

### ● Rated continuous Working Voltage (RCWV)


$$= \sqrt{\text{power rating} \times \text{resistance value}}$$



**SYNTECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	12/16
Date :	2006.01.01

### 8. COLOR CODING



Color	1st, 2nd 3rd (Significant Figure)			(Multiplier)	(Tolerance)
Black	0	0	0	$10^0$	
Brown	1	1	1	$10^1$	F ( $\pm 1\%$ )
Red	2	2	2	$10^2$	G ( $\pm 2\%$ )
Orange	3	3	3	$10^3$	
Yellow	4	4	4	$10^4$	
Green	5	5	5	$10^5$	D ( $\pm 0.5\%$ )
Blue	6	6	6	$10^6$	C ( $\pm 0.25\%$ )
Violet	7	7	7	$10^7$	B ( $\pm 0.1\%$ )
Gray	8	8	8	$10^8$	A ( $\pm 0.05\%$ )
White	9	9	9	$10^9$	AA ( $\pm 0.01\%$ )
Gold				$10^{-1}$	J ( $\pm 5\%$ )
Silver				$10^{-2}$	

Figure6



**SYNTECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	13/16
Date :	2006.01.01



**Test Report**

SYNTECH CORPORATION  
 16F-3, NO. 79, FAR EAST WORLD CENTER SEC. 1, HSIIN  
 TAI WU ROAD, HSI-CHIH TAIPEI HSIEN, TAIWAN, R. O. C.  
 DONG GUAN PLANT  
 SHUI KOU INDUSTRIAL ZONE, DA LANG,  
 DNG GUAN, GUANG DONG, CHINA

Report No. : CE/2006/73556  
 Date : 2006/07/19  
 Page : 1 of 4



The following sample(s) was/were submitted and identified by/on behalf of the client as :

Sample Description : METAL FILM FIXED RESISTORS (EPOXY COATING)  
 Style/Item No : MF, FMF TYPE  
 Sample Received : 2006/07/12  
 Testing Period : 2006/07/12 TO 2006/07/19

=====  
Test Result(s) : - Please see the next page(s) -

Daniel Yen, M.R., Operation Manager  
 Signed for and on behalf of  
 SGS TAIWAN LTD.

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGS TAIWAN LIMITED NO. 156-1, Wu Kung Road, WuKu Industrial Zone, Taipei county, Taiwan.  
 1(886-2) 22903930 1(886-2) 2290-3237 www.sgs.com.tw

*Confidential, Do Not Disseminate.*



**SYNTECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.: MF-02  
Version: A  
Page: 14/16  
Date : 2006.01.01



**Test Report**

SYNTECH CORPORATION  
16F-3, NO. 79, FAR EAST WORLD CENTER SEC. 1, HSIIN  
TAI WU ROAD, HSI-CHIH TAIPEI HSIEN, TAIWAN, R. O. C.  
DONG GUAN PLANT  
SHUI KOU INDUSTRIAL ZONE, DA LANG,  
DNG GUAN, GUANG DONG, CHINA

Report No. : CE/2006/73556  
Date : 2006/07/19  
Page : 2 of 4



**Test Result(s)**

PART NAME NO.1 : MIXED ALL PARTS OF BLUE BODY

Test Item (s):	Unit	Method	MDL	Result No.1
<b>PBBs (Polybrominated biphenyls)</b>	---	---	---	---
Monobromobiphenyl	%	With reference to USEPA3540C. Analysis was performed by HPLC/DAD, LC/MS or GC/MS. (prohibited by 2002/95/EC (RoHS), 83/264/EEC, and 76/769/EEC)	0.0005	N.D.
Dibromobiphenyl	%		0.0005	N.D.
Tribromobiphenyl	%		0.0005	N.D.
Tetrabromobiphenyl	%		0.0005	N.D.
Pentabromobiphenyl	%		0.0005	N.D.
Hexabromobiphenyl	%		0.0005	N.D.
Heptabromobiphenyl	%		0.0005	N.D.
Octabromobiphenyl	%		0.0005	N.D.
Nonabromobiphenyl	%		0.0005	N.D.
Decabromobiphenyl	%		0.0005	N.D.
<b>Total PBBs (Polybrominated biphenyls)/Sum of above</b>	%		-	N.D.
<b>PBBes(PBDEs) (Polybrominated biphenyl ethers)</b>	---	---	---	---
Monobromobiphenyl ether	%	With reference to USEPA3540C. Analysis was performed by HPLC/DAD, LC/MS or GC/MS. (prohibited by 2002/95/EC (RoHS), 83/264/EEC, and 76/769/EEC)	0.0005	N.D.
Dibromobiphenyl ether	%		0.0005	N.D.
Tribromobiphenyl ether	%		0.0005	N.D.
Tetrabromobiphenyl ether	%		0.0005	N.D.
Pentabromobiphenyl ether	%		0.0005	N.D.
Hexabromobiphenyl ether	%		0.0005	N.D.
Heptabromobiphenyl ether	%		0.0005	N.D.
Octabromobiphenyl ether	%		0.0005	N.D.
Nonabromobiphenyl ether	%		0.0005	N.D.
Decabromobiphenyl ether	%		0.0005	N.D.
<b>Total PBBes(PBDEs) (Polybrominated biphenyl ethers)/Sum of above</b>	%		-	N.D.
<b>Total of Mono to Nona-brominated biphenyl ether. (Note 4)</b>	%		-	N.D.

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGS TAIWAN LIMITED NO. 138-1, Wu Kung Road, WuKia Industrial Zone, Taipei county, Taiwan. t(886-2) 22903939 f(886-2) 2290-3237 www.sgs.com.tw



**SYNTECH CORPORATION**  
**METAL FILM FIXED RESISTORS**

File No.:	MF-02
Version:	A
Page:	15/16
Date :	2006.01.01



**Test Report**

SYNTECH CORPORATION  
 16F-3, NO. 79, FAR EAST WORLD CENTER SEC. 1, HSIIN  
 TAI WU ROAD, HSI-CHIH TAIPEI HSIEN, TAIWAN, R. O. C.  
 DONG GUAN PLANT  
 SHUI KOU INDUSTRIAL ZONE, DA LANG,  
 DNG GUAN, GUANG DONG, CHINA

Report No. : CE/2006/73556  
 Date : 2006/07/19  
 Page : 3 of 4



Test Item (s):	Unit	Method	MDL	Result
				No. 1
Chromium VI (Cr+6)	ppm	UV-VIS(US EPA 7196A) after reference to US EPA 3060A.	2	N.D.
Cadmium (Cd)	ppm	ICP-AES after reference to US EPA 3052 or other acid digestion.	2	N.D.
Mercury (Hg)	ppm	ICP-AES after reference to US EPA 3052 or other acid digestion.	2	N.D.
Lead (Pb)	ppm	ICP-AES after reference to US EPA 3052 or other acid digestion.	2	N.D.

- NOTE: (1) N.D. = Not Detected (<MDL)  
 (2) ppm = mg/kg  
 (3) MDL = Method Detection Limit  
 (4) Decabromobiphenyl ether (DecaBDE) in polymeric applications is exempted by Commission Decision of 13 Oct 2005 amending Directive 2002/95/EC notified under document 2005/717/EC.  
 (5) PBBEs=PBDEs=Polybrominated Diphenyl Ethers=PBDOs=PBBOs.  
 (6) " - " = Not Regulation  
 (7) " --- " = Not Applicable

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGS TAIWAN LIMITED NO. 136-1, Wu Kung Road, WuKu Industrial Zone, Taipei county, Taiwan.  
 1(886-2) 22909339 1(886-2) 2290-3237 www.sgs.com.tw

*Confidential, Do Not Disseminate.*





**SYNTECH CORPORATION**  
**METAL FILM FIXED RESISTORS**


File No.:	MF-02
Version:	A
Page:	16/16
Date :	2006.01.01



### Test Report

SYNTECH CORPORATION  
16F-3, NO. 79, FAR EAST WORLD CENTER SEC. 1, HSIEN  
TAI WU ROAD, HSI-CHIH TAIPEI HSIEN, TAIWAN, R. O. C.  
DONG GUAN PLANT  
SHUI KOU INDUSTRIAL ZONE, DA LANG,  
DNG GUAN, GUANG DONG, CHINA

Report No. : CE/2006/73556  
Date : 2006/07/19  
Page : 4 of 4



\*\* End of Report \*\*

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGS TAIWAN LIMITED

NO. 138-1, Wu Kung Road, WuKu Industrial Zone, Taipei county, Taiwan.  
t(886-2) 22969898 f(886-2) 2296-3237 www.sgs.com.tw

*Confidential, Do Not Disseminate.*